

Preparation of biuret-containing polyisocyanates

Abstract

5


A process for the preparation of polyisocyanates which contain one or more biuret groups, by reacting

- 10 a) an aliphatic or cycloaliphatic isocyanate containing two or more isocyanate groups (isocyanate a) with
- b) a tertiary alcohol or a mixture of water and a tertiary alcohol (biuretizing agent b)

15 at from 100 to 250°C, which comprises carrying out the reaction in the presence

- c) of a stabilizer (c) which constitutes a catalytic amount of urea, ammonia, biuret, a urea derivative of the formula I

20



25

in which R¹, R², R³ and R⁴ are hydrogen, C₁ to C₁₀ alkyl or C₅ to C₁₀ aryl, or

a carboxamide of the formula II


30



35

in which R⁵ is C₁ to C₁₂ alkyl which is unsubstituted or in which 1, 2 or 3 hydrogen atoms are replaced by a radical

40



45

0050456 00159 45630 95746330